



## Provisional Technical Datasheet

### F03RR Polypropylene Homopolymer

### BOPP Films

#### Product Characteristics:

Polysure F03RR is Polypropylene Homopolymer, produced by Latest Novolen Technology & Primarily suitable for BOPP Stenter Process Applications. F03RR combines narrow MFR specification range especially for OPP core layers. The product is free from metal stearates and functional additives like slip agents and is therefore in particular suitable for metallisable BOPP film and provides low water-carry-over

#### Recommended Applications:

F03RR is recommended for General Purpose BOPP Films, Metallizable BOPP Films (Stenter process) & lamination grade BOPP Films.

#### Typical Properties:

Sr. No.	Properties	Test Method	Units	Values*
1	Melt Flow Index ( 230°C & 2.16 kg)	ASTM D1238	g/10 min	3.2
2	Tensile Strength @ Yield (50mm / min)	ASTM D638	MPa	34
3	Tensile Elongation @ Yield (50mm / min)	ASTM D638	%	9
4	Flexural Modulus	ASTM D790	MPa	1450
5	Notch Izod Impact Strength ( 23°C)	ASTM D256	J/m	40
6	Vicat Softening Point (10N)	ASTM D1525	°C	154
7	Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	95

\*All the mechanical properties as per ASTM D638 Type I Injection molded specimen prepared in accordance with ASTM D 4101

#### Processing Guidelines:

- Barrel Temperature : 230 - 280°C
- Quench Temperature : 10-15°C

#### Storage & Handling:

Bags should be stored in dry & dust free environment at temperature below 50 °C and Prevent from direct exposure to sunlight & heat to avoid quality deterioration.

#### Regulatory Requirements:

F03RR is manufactured complying the requirements specified in IS 10910 on "Specification for Polypropylene & its Copolymers for safe use in contact with Foodstuff, Pharmaceutical & Drinking water". Furthermore the Additives added in this grade formulation compiles to the "Positive list of constituents of Polypropylene and its Copolymers in contact with Foodstuff, Pharmaceutical & Drinking water" as laid down under IS 10909. In general the additives & constituents used in the grade are in line with requirement laid down under FDA: CFR Title 21,177.1520, Olefin Polymers.

**Disclaimer:** The information & data presented herein are typical values & should not be considered as specification and may be used as guideline only. HMEL does not undertake any responsibility for any outcome or results from the adoption or replication of the above mentioned data & information there on for possible use for various applications. HMEL reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage.

HPCL-Mittal Energy Limited (HMEL), INOX Tower, Plot No.17, Sector-16A, Noida – 201301 (U.P), India. Tel: 0120-4634500. Corporate Site: [www.hmel.in](http://www.hmel.in)